

## Test Report

No.: SHHG1106017145BM

Date: JUL.08,2011

Page: 1 of 3

AGILENT INTERNATIONAL CO., LIMITED

MSH 2896 RM 1007, 10/F HO KING CTR 2-16 FA YUEN ST. MONG KOK KL. HK

The following sample(s) was/were submitted and identified by the client as:

Sample Description : LAMINATE FLOORING  
Style/ Item No. : FORTHFLOOR PRATIC  
P.O. No. : LOTE 65  
Country of Origin : CHINA  
Sample Receiving Date : JUL.04,2011  
Testing Period : JUL.04,2011 TO JUL.08,2011  
Test Performed : SELECTED TEST(S) AS REQUESTED BY APPLICANT  
Test Requested : ABRASION RESISTANCE (REFER TO EN 13329-2006+A1:2008 ANNEX E)  
Test Result(s) : FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)  
Conclusion : THE SUBMITTED SAMPLE MET THE TEST REQUIREMENT.

\*\*\*\*\*

Signed for and on behalf of  
SGS-CSTC Ltd.



Yomoro Gu  
Supervisor

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



3<sup>rd</sup> Building, No. 889, Yishan Road, Xuhui District Shanghai, China 200233  
中国·上海·徐汇区宜山路889号3号楼

t (86-21)61402666\*2013  
t (86-21)61402666\*2013

f (86-21)54500353  
f (86-21)54500353  
e [sgs.china@sgs.com](mailto:sgs.china@sgs.com)

**Test Conducted:**

**Abrasion resistance (Refer to EN 13329-2006+A1:2008 Annex E)**

Test Item	Test Method/Requirement	Rating/ Result																																		
<b>EN 13329:2006+A1:2008 Annex E</b>																																				
<b>Abrasion resistance</b>	<p>Prepare two wheels with preconditioned unused abrasive paper from the same batch previously approved by calibration.</p> <p>Lower the wheels, start the suction device and abrade the test specimen.</p> <p>Examine the test specimen for abrasion after each 100 revolutions and renew the abrasive papers after every 200 revolutions.</p> <p>Continue the test in this way until the initial wear point (IP) is reached. The initial wear point is reached when there are areas of at least 0.60 mm<sup>2</sup> wear-through in two quadrants and an area of 0.60 mm<sup>2</sup> wear-through becomes visible in a third quadrant.</p> <p>Record the number of revolutions as the IP-value. Repeat the test immediately using the two remaining tests immediately using the two remaining test specimens.</p>	<p>Pass</p> <p>Claimed Abrasion class: AC3</p> <p>Measured Abrasion class: AC4 (Average IP value:4000)</p>																																		
	<table border="1"> <tr> <td>Abrasion class</td> <td>AC1</td> <td>AC2</td> <td>AC3</td> <td>AC4</td> <td>AC5</td> <td>AC6</td> </tr> <tr> <td>Average IP-value</td> <td>≥90 0</td> <td>≥150 0</td> <td>≥200 0</td> <td>≥400 0</td> <td>≥600 0</td> <td>8500</td> </tr> </table>	Abrasion class	AC1	AC2	AC3	AC4	AC5	AC6	Average IP-value	≥90 0	≥150 0	≥200 0	≥400 0	≥600 0	8500																					
	Abrasion class	AC1	AC2	AC3	AC4	AC5	AC6																													
	Average IP-value	≥90 0	≥150 0	≥200 0	≥400 0	≥600 0	8500																													
<p><b>Classification requirements for Class 21(Domestic Moderate) to Class 33 (Commercial Heavy)</b></p> <p><b>Requirement:</b></p> <table border="1"> <thead> <tr> <th colspan="7">Levels of use</th> </tr> <tr> <th colspan="3">Domestic</th> <th colspan="4">Commercial</th> </tr> <tr> <th>Mod.</th> <th>Gen.</th> <th>Hea.</th> <th>Mod.</th> <th>Gen.</th> <th>Hea</th> <th>V.Hea</th> </tr> </thead> <tbody> <tr> <td>21</td> <td>22</td> <td>23</td> <td>31</td> <td>32</td> <td>33</td> <td>34</td> </tr> <tr> <td>AC1</td> <td>AC2</td> <td>AC3</td> <td>AC3</td> <td>AC4</td> <td>AC5</td> <td>AC6</td> </tr> </tbody> </table>	Levels of use							Domestic			Commercial				Mod.	Gen.	Hea.	Mod.	Gen.	Hea	V.Hea	21	22	23	31	32	33	34	AC1	AC2	AC3	AC3	AC4	AC5	AC6	
Levels of use																																				
Domestic			Commercial																																	
Mod.	Gen.	Hea.	Mod.	Gen.	Hea	V.Hea																														
21	22	23	31	32	33	34																														
AC1	AC2	AC3	AC3	AC4	AC5	AC6																														

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



## Test Report

No.: SHHG1106017145BM

Date: JUL.08,2011

Page: 3 of 3

### Sample Photo:

Test sample (front View)



Test sample (back View) (FORTHFLOOR PRATIC AC3 CHINA 2011 05 2109:53:06 65)



\*\*\*End of Report\*\*\*

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and, within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.